

352 CONSTRUCTION SPECIFICATION FOR CONCRETE STEPS**352.02 References****Canadian Standards Association:**

CSA A23.1-94/A23.2-94 Concrete Materials and Methods of Concrete Construction/Methods of Test for Concrete

352.05.01 Concrete

Delete section in its entirety.

Add in the following:

Concrete shall be according to OPSS 1350, with a minimum specified 28-Day compressive strength of 35 MPa, Class C-1 Exposure. Coarse aggregate for the concrete shall have a nominal maximum size of 19.0 mm.

352.09.01.01 Concrete Steps

Delete paragraph.

Add in the following:

Measurement for payment shall be in cubic metres of the concrete placed, based on the neat lines called for in the contract.