

1150 MUNI MATERIAL SPECIFICATION FOR HOT MIX ASPHALT

ADD in the following subsection:

1150.02 References

ADD in the following:

OPSS 102 General Specification for Weighing of Materials

1150.04.01.02.03 Changes to the Job-Mix Formula and the Mix Design

DELETE in its entirety.

ADD the following:

Changes to the JMF shall be permitted subject to the conditions specified in GSSS 310.

A new mix design shall be completed according to the Mix Design clause, when:

- a) A material is eliminated.
- b) A new material is added.
- c) A material source is changed.
- d) The net impact of all adjustments to the original JMF exceeds any of the maximum field adjustments according to Table 8.
- e) The allowable time period has been exceeded and the use of the mix design has not been extended.

The allowable time period has been exceeded and the use of the mix design has not been extended.

1150.05.02.05 Heavy Duty Binder Course (HDBC)

ADD the following:

"All reference to crushed bedrock material shall also mean particles produced by crushing gravel, cobbles or boulders retained by the 50.0 mm sieve having a minimum of 95% of crushed materials with two (2) fractured faces.

1150.08.01 General

ADD in the following:

- Note 2 of Table II Gradation Requirements - Mix Design Criteria is amended to read: "HDBC shall contain 30 to 52 percent by volume of the total aggregates passing the 4.75 mm sieve."
- Table III, Asphalt Cement Content - Mix Design Criteria is amended to read: "4.7% Asphalt Cement Content (minimum by mass of mixture) for HDBC hot mix type."

1150-01